(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 8 July 2004 (08.07.2004)

PCT

(10) International Publication Number WO 2004/057261 A1

(51) International Patent Classification7: C22C 21/00

F28F 21/08,

Thiagarajan [CA/US]; 19170 Tanglewood, North Royal-

(21) International Application Number:

PCT/CA2003/002002

(22) International Filing Date:

22 December 2003 (22.12.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/436,022

23 December 2002 (23.12.2002)

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application:

US

60/436,022 (CIP)

Filed on

23 December 2002 (23.12.2002)

- (71) Applicant (for all designated States except US): ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street West, Montreal, Québec H3A 3G2 (CA).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): PARSON, Nicholas, Charles [GB/CA]; 1659 Grousewood Lane, Kingston, Ontario K7L 5H6 (CA). GRAY, Alan [GB/GB]; 5 Red House Road, Bodicote, Banbury, Oxfordshire OX15 4BB (GB). MAROIS, Pierre, Henri [CA/CA]; 859 Old Colony Road, Kingston, Ontario K7P 1S1 (CA). RAMANAN,

ton, OH 44133 (US).

- (74) Agents: EADES, Norris, M. et al.; Kirby Eades Gale Baker, Box 3432, Station D., Ottawa, Ontario K1P 6N9 (CA).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ALUMINUM ALLOY TUBE AND FIN ASSEMBLY FOR HEAT EXCHANGERS HAVING IMPROVED CORRO-SION RESISTANCE AFTER BRAZING

(57) Abstract: Extruded tubes for heat exchangers have improved corrosion resistance when used alone and when part of a brazed heat exchanger assembly with compatible finstock. The tubes are formed from a first aluminum alloy comprising 0.4 to 1.1% by weight manganese, up to 0.01% by weight copper, up to 0.05% by weight zinc, up to 0.2% by weight iron, up to 0.2% by weight silicon, up to 0.01% by weight nickel, up to 0.05% by weight titanium and the balance aluminum and incidental impurities. The fins are formed from a second aluminum alloy containing 0.9 to 1.5% by weight manganese or an alloy of the AA3003 type, this second aluminum alloy further containing at least 0.5% by weight zinc.

